

HG POLYESTER FABRIC



PRODUCT DESCRIPTION

HG POLYESTER FABRIC is a spunbond 100% polyester (PET) fabric. It is used as reinforcement for the **HYDRO-TUFF HFA** membrane. It is used in detail work such as crack reinforcement, construction joints and reinforcement for inside and outside corners. It is also used as a fully embedded reinforcement into the **HYDRO-TUFF HFA** for the 215 mil fully reinforced membrane. Detailing drains, expansion joints and large cracks are not appropriate for the fabric. Neoprene flashing must be used for these conditions.

PHYSICAL PROPERTIES

<u>Description</u>	<u>Test Method</u>	<u>Results</u>
Weight	ASTM D3776	1.35 /oz/sy
Grab Tensile	ASTM D5034	MD: 21 lbf CD: 18 lbf
Grab Elongation	ASTM D5034	MD: 43% CD: 66%
Mullen Burst		27 psi

PACKAGING

Roll Sizes: Widths - 36"
 Lengths- 750'

INSTALLATION

HG POLYESTER FABRIC is installed in a multitude of fashions. Contact the manufacturer for specific installation instructions.

AVAILABILITY

HG POLYESTER FABRIC is available from the manufacturer, vendors, or factory trained contractors.

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience. For the most up to date information, please visit www.hydro-gard.com. HYDRO-GARD accepts no responsibility for the results obtained through application of this product. HYDRO-GARD reserves the right to update information without notice.

HYDRO-GARD LLC • 18340 Yorba Linda Blvd. Suite 107, Box 304, Yorba Linda, Ca 92886

Tel 562/ 944-7030 • Fax 562/ 944-6402 • www.hydro-gard.com