


1. Substrate
2. GARD-DECK Primer 112
3. 1st Layer GARD-DECK 800 R (w/ Quartz Sand, slightly broadcast)
- allow to cure 45-60 min.
4. 2nd Layer GARD-DECK 800 R (w/ Quartz Sand, slightly broadcast)
- allow to cure 45-60 min.
5. 3rd Layer GARD-DECK 800 R (w/ GARD DECK-FLEECE 3.0, Embed)
- allow to cure 45-60 min.
6. 4th Layer GARD-DECK 800 R (w/ Quartz Aggregates)
- broadcast Quartz Aggregates to full refusal
- fully cure, sweeping excess Quartz Aggregates
7. GARD-DECK 528C Sealer (Colored top coat)



DETAIL NAME:

**GARD-DECK TRAFFIC COATING SYSTEM
(Reinforced)**

JOB NAME:

Scale:

NTS

Date:

04-17-17

Drawing #:

GD-001