

## **PRODUCT DESCRIPTION**

Gard-Deck® Mortar 50/51 is a high quality pre-assembled mortar system for repairs to spalled concrete and other concrete repair. It is a methal methacrylic base product with the fillers, liquid and hardener in one packaged product.

# **PRODUCT USE**

Gard-Deck® Mortar 50/51 is primarily use for concrete substrate repair prior to the installation of the Gard-Deck® membrane applications. Loose and or spalled concrete cracks, and or areas of concrete which have voids are to be chipped out to clean concrete primed with Gard-Deck® primer 112 and then filled with Gard-Deck® Mortar 50/51 patching material.

# PACKAGING

Kits Contain: 1- 55 lb Bag, Powder (Catalyst) and Mortar

## APPLICATION

After complete removal and cleaning of spalled concrete remove all loose particles and sweep or blow out cavity space of repair area. Prime all surfaces for the application of Gard-Deck® 50/51 with Gard-Deck® 112 primer. Let primer cure per Gard-Deck® 112 primer application guide. Mix components of Gard-Deck® 50/51 and install into the spalled / repair area to desired thickness and finish. Application must be installed in layers not to exceed 3/8" per layer of application. All cured repaired areas of Gard-Deck® 50/51 must be primed with Gard-Deck® 112 prior to resin applications of Gard-Deck® Traffic Coating Systems. Allow 1.5 to 2 hours of curing time prior to installation of Gard-Deck® 112 primer.

### STORAGE

Store Gard-Deck® 50/51 in a cool and dry environment. Keep out of direct sunlight and maintain temperature between 60 - 75 °F.

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience. For the most up to date information, please visit www.hydro-gard.com. HYDRO-GARD accepts no responsibility for the results obtained through application of this product. HYDRO-GARD reserves the right to update information without notice.